

Test Report

No. AJFS1804003399FF

Date: APR.26, 2018

Page 1 of 5

SIJIA NEW MATERIAL (SHANGHAI) CO., LTD

SIJIA INDUSTRIAL PARK NO.8 QIUZHEN ROAD, CAOJING TOWN, JINSHAN DISTRICT, SHANGHAI, CHINA

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: PVC COATING MATERIAL

SGS Ref No.: SUIN1804002601SC

Product Specification: 850gsm/R9003AA

Test Requested:

NF P 92-507:2004 Fire safety-building-interior fitting materials-Classification according to their reaction to fire

Test Results: -- See attached sheet --

Conclusion:

Classification: M2

Note: The classes with their corresponding fire performance are given in Annex I.

Test Period:

Sample Receiving Date : APR.16, 2018

Test Performing Date : APR.16, 2018 TO APR.24, 2018

Signed for and on behalf of
SGS-CSTC Co., Ltd. Anji Branch

Allen Zou
Technical Manager



SGS-CSTC Inspection & Testing Services Co., Ltd.
Anji Branch Harbin

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

I. Test conducted

This test was conducted according to NF P 92-507:2004 Fire safety-building-interior fitting materials - Classification according to their reaction. And the test methods as following:

NF P 92-503:1995 Safety against fire—Building materials—Reaction to fire tests—Electrical burner test used for flexible materials.

II. Details of classified product

Sample description	PVC
Color	White
Area Density	About 875 g/m ²
Specimen size	600mm×180mm

III. Conditioning

Prior to testing, the sample was conditioned,

In an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5% for 7 days or until constant mass is obtained. The mass is considered as constant when two successive weightings 24 hours apart do not differ by more than 0.1% or 0.1 g (take the highest mass value).

IV. Test results

NF P 92-503:1995 Electrical burner test

Exposed face identification: Face, Orientation: Weft (if applicable)

During the testing, the following details are noted	Sample 1	Sample 2	Sample 3	Sample 4
Hole (Yes/No)	Yes	Yes	Yes	Yes
Max. afterflame time after withdrawal the pilot flame (s)	186	152	160	189
Afterglow time (s)	-	-	-	-
Flaming molten droplets (Yes/No)	No	No	No	No
Non-flaming molten droplets (Yes/No)	No	No	No	No
Flaming debris (Yes/No)	No	No	No	No
Non-flaming debris (Yes/No)	No	No	No	No
White-hot spots with propagation effects (Yes/No)	No	No	No	No

To be continued....



After testing, the following details are noted;	Sample 1	Sample 2	Sample 3	Sample 4
Max. destruction length from the lower edge (cm)	33	34	33	32
Average length (cm)	33			
Max. width of the destroyed zones between 450mm and 600mm from the test piece lower edge (cm)	ND	ND	ND	ND
Average width (cm)	ND			

Remark: "ND" indicates Non-detected

Annex I, Classification

Table 1 Resume of classification for flexible materials which thickness no more than 5mm

Test Items	Criteria of classification				
		No ignition of the wadding	No ignition of the wadding	Ignition of the wadding	Ignition of the wadding
Test for hot melt materials		No ignition of the wadding	No ignition of the wadding	Ignition of the wadding	Ignition of the wadding
Electrical Burner Test ^{a)}	No drops	Non-flaming molten droplets	Flaming drops or debris	Non-flaming molten droplets	Flaming drops or debris
Inflammation ≤ 5s	M1	M1	M2	M4	M4
Inflammation > 5s and Average destroyed length <350 mm	M2	M2	M3	M4	M4
Inflammation > 5s and Average destroyed width <90 mm between the 450 mm and 600 mm in length	M3	M3	M4	M4	M4
Flame Spread Test (flame spread <2 mm/s)			M4	M4	M4

^{a)} If the materials presented a particular behaviour, the classification also needs to refer to Table 3. The details of classification M0 refer to clause 3.3 of NF P 92-507:2004.

To be continued....



Table 3 Resume of classification for the materials presented a particular behaviour

Test Items	Criteria of classification				
<u>Test for hot melt materials</u>		Not ignite the wadding	Not ignite the wadding	Ignite the wadding	Ignite the wadding
<u>Flame Persistence Test</u>	No drops	Non-flaming molten drops	Flaming drops or debris	Non-flaming molten drops	Flaming drops or debris
Flame persistence time ≤ 2s	M1	M1	M2	M4	M4
Flame persistence time ≤ 5s	M2	M2	M3	M4	M4
Flame persistence time > 5s and Flame Spread < 2 mm/s	M3	M3	M4	M4	M4

STATEMENTS:

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test. They are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product, which is supplied or used, is fully represented by the specimens, which were tested.

The specimen was supplied by the sponsor and SGS-CSTC ANJI Branch was not involved in any selection or sampling procedure.


Remark: The test report shall only be used for client internal reference.

To be continued....



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Photo Appendix:



SGS authenticate the photo on original report only

End of Report

